

ABSTRACT

A vulcanizable adhesive composition, which comprises 100 parts by weight of phenolxylylene resin or phenolbiphenyl resin, 10 to 1,000 parts by weight of resol-type phenol resin, 0 to 1,000 parts by weight of novolak-type phenol resin, 10 to 1,000 parts by weight of unvulcanized nitrile rubber and 10 to 500 parts by weight of chlorinated polyethylene, is effectively applied to (hydrogenated) nitrile rubber with a nitrile content of 18 to 48%, and has a suppression effect on a decrease in the adhesiveness even if exposed to dip in various cryogenic liquids such as flon gas, polyalkylene glycol, water, etc. for a long time.

(19) 世界知的所有権機関
国際事務局



(43) 国際公開日
2005年3月17日 (17.03.2005)

PCT

(10) 国際公開番号
WO 2005/023952 A1

(51) 国際特許分類: C09J 165/00,
161/08, 109/02, B32B 15/06, 25/14

(21) 国際出願番号: PCT/JP2003/010829

(22) 国際出願日: 2003年8月27日 (27.08.2003)

(25) 国際出願の言語: 日本語

(26) 国際公開の言語: 日本語

(71) 出願人 (米国を除く全ての指定国について): NOK
株式会社 (NOK CORPORATION) [JP/JP]; 〒105-8585
東京都港区芝大門一丁目12-15 Tokyo (JP).

(72) 発明者; および

(75) 発明者/出願人 (米国についてのみ): 深澤 清文 (FUKA-
SAWA, Kiyofumi) [JP/JP]; 〒251-0042 神奈川県 藤沢市
辻堂新町四丁目3-1 NOK株式会社内 Kanagawa (JP).
貝瀬 友宏 (KAISE, Tomohiro) [JP/JP]; 〒251-0042 神奈
川県 藤沢市 辻堂新町四丁目3-1 NOK株式会社内
Kanagawa (JP).

(74) 代理人: 吉田 俊夫, 外 (YOSHIDA, Toshio et al.); 〒
150-0022 東京都 渋谷区恵比寿南一丁目21-11 ヒルサ
イド恵比寿202 吉田特許事務所 Tokyo (JP).

(81) 指定国 (国内): AE, AG, AL, AM, AT, AU, AZ, BA, BB,
BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK,
DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU,
ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT,
LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO,
NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK,
SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC,
VN, YU, ZA, ZM, ZW.

(84) 指定国 (広域): ARIPO 特許 (GH, GM, KE, LS, MW, MZ,
SD, SL, SZ, TZ, UG, ZM, ZW), ユーラシア特許 (AM,
AZ, BY, KG, KZ, MD, RU, TJ, TM), ヨーロッパ特許
(AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB,
GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR),
OAPI 特許 (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

添付公開書類:

- 国際調査報告書
- 補正書・説明書

2文字コード及び他の略語については、定期発行される
各PCTガゼットの巻頭に掲載されている「コードと略語
のガイダンスノート」を参照。

(54) Title: VULCANIZABLE ADHESIVE COMPOSITION

(54) 発明の名称: 加硫接着剤組成物

(57) Abstract: A vulcanizable adhesive composition which comprises 100 parts by weight of a phenol-xylylene resin or phenol-biphenyl resin, 10 to 1,000 parts by weight of a resol resin, 0 to 1,000 parts by weight of a phenolic novolak, 10 to 1,000 parts by weight of a green nitrile rubber, and 10 to 500 parts by weight of chlorinated polyethylene. This vulcanizable adhesive composition is effectively applicable to (hydrogenated) nitrile rubbers having a nitrile content of 18 to 48%. It is prevented from decreasing in adhesiveness even when immersed for long in various refrigerants such as a fluorocarbon gas, polyalkylene glycol, and water.

(57) 要約: フェノールキシレリン樹脂またはフェノールビフェニル樹脂100重量部、レゾール型フェノール樹脂約10~1000重量部、ノボラック型フェノール樹脂0~1000重量部、未加硫のニトリルゴム10~1000重量部および塩素化ポリエチレン10~500重量部を含有してなる加硫接着剤組成物。この加硫接着剤組成物は、ニトリル含量が18~48%の(水素化)ニトリルゴムに有効に使用され、さらにフロンガス、ポリアルキレングリコールまたは水などの各種冷媒に長時間浸せきした場合にもその接着性の低下が抑えられる。

WO 2005/023952 A1